

TECHNICAL DATA SHEET

PRODUCT: WHITE FUSED ALUMINA

White Fused alumina was made from the high quality alumina by melting above 2000 in the electric arc furnace and cooling. It is white with the main crystal phase α -Al₂O₃.

AVERAGE CHEMICAL COMPOSITION(TYPICAL)

Al ₂ O ₃	≥99.5%
Na ₂ O	≤0.35%
Fe ₂ O ₃	≤0.06%

PHYSICAL PROPERTIES(TYPICAL)

Specific Gravity	≥3.90g/cm ³
Mohs Hardness	9.0
Bulk Density	1.75-1.95g/cm ³
Melting Point	2250°C

PACKAGING:25kgs PVC bags+1MT big bag

PARTICLE SIZE DISTRIBUTION

F8	+4000um	0	+2800um	≤20%	+2360um	≥45%	+2360+2000um	≥70%	-1700um	≤3%
F10	+3350um	0	+2360um	≤20%	+2000um	≥45%	+2000+1700um	≥70%	-1400um	≤3%
F12	+2800um	0	+2000um	≤20%	+1700um	≥45%	+1700+1400um	≥70%	-1180um	≤3%
F14	+2360um	0	+1700um	≤20%	+1400um	≥45%	+1400+1180um	≥70%	-1000um	≤3%
F16	+2000um	0	+1400um	≤20%	+1180um	≥45%	+1180+1000um	≥70%	-850um	≤3%
F20	+1700um	0	+1180um	≤20%	+1000um	≥45%	+1000+850um	≥70%	-710um	≤3%
F22	+1400um	0	+1000um	≤20%	+850um	≥45%	+850+710um	≥70%	-600um	≤3%
F24	+1180um	0	+850um	≤25%	+710um	≥45%	+710+600um	≥65%	-500um	≤3%
F30	+1000um	0	+710um	≤25%	+600um	≥45%	+600+500um	≥65%	-425um	≤3%
F36	+850um	0	+600um	≤25%	+500um	≥45%	+500+425um	≥65%	-355um	≤3%
F46	+600um	0	+425um	≤30%	+355um	≥40%	355+300um	≥65%	-250um	≤3%
F54	+500um	0	+355um	≤30%	+300um	≥40%	+300+250um	≥65%	-212um	≤3%
F60	+425um	0	+300um	≤30%	+250um	≥40%	250+212um	≥65%	-180um	≤3%
F70	+355um	0	+250um	≤25%	+212um	≥40%	+212+180um	≥65%	-150um	≤3%
F80	+300um	0	+212um	≤25%	+180um	≥40%	+180+150um	≥65%	-125um	≤3%
F90	+250um	0	+180um	≤20%	+150um	≥40%	+150+125um	≥65%	-106um	≤3%
F100	+212um	0	+150um	≤20%	+125um	≥40%	+125+106um	≥65%	-75um	≤3%
F120	+180um	0	+125um	≤20%	≥40%	≥40%	+106+90um	≥65%	-63um	≤3%
F150	+150um	0	+106um	≤15%	+75um	≥40%	+75+63um	≥65%	-45um	≤3%
F180	+125um	0	+90um	≤15%	+75um	*	+75+63um	≥40%	-53um	*
F220	+106um	0	+75um	≤15%	+63um	*	+63+53um	≥40%	-45um	*

ZHENGZHOU HAIXU ABRASIVES CO.,LTD

CONTACT:SUNSHINE MA **EMAIL:**SALES@ZZHAIXU.CN **MP/WECHAT/WHATS APP:**+8615838373120

<http://wfacn.com>